

## **EP0084395A1**

Publication Title:

Artificial heart valves.

Abstract:

Abstract not available for EP 0084395

(A1)

-----

Courtesy of <http://v3.espacenet.com>



Europäisches Patentamt  
European Patent Office  
Office européen des brevets

(11) Publication number:

**0 084 395**  
**A1**

(12)

## EUROPEAN PATENT APPLICATION

(21) Application number: 83200046.7

(51) Int. Cl.<sup>3</sup>: A 61 F 1/22

(22) Date of filing: 13.01.83

(30) Priority: 20.01.82 GB 8201793

(43) Date of publication of application:  
27.07.83 Bulletin 83/30

(84) Designated Contracting States:  
AT BE CH DE FR GB IT LI LU NL SE

(71) Applicant: Black, Martin Morris  
26 Broad Elms Lane  
Sheffield, S11 9RQ(GB)

(71) Applicant: Drury, Philip John  
43 Winchester Crescent  
Sheffield, S10 4ED(GB)

(71) Applicant: THE UNIVERSITY OF SHEFFIELD  
Western Bank  
Sheffield, S10(GB)


(72) Inventor: Black, Martin Morris  
26 Broad Elms Lane  
Sheffield S11 9RQ(GB)

(72) Inventor: Drury, Philip John  
43 Winchester Crescent  
Sheffield S10 4ED(GB)

(74) Representative: Hulse, Thomas Arnold et al,  
Hulse & Co. Cavendish Buildings West Street  
Sheffield S1 1ZZ(GB)

(54) Artificial heart valves.

(57) A bioprosthetic mitral valve replacement comprises a flexible frame (1) having a ring-shaped base (2) and at least a pair of upstanding posts (3), which divide the base into at least two portions (2A, 2B) of varying flexibility, together with animal tissue leaflets (4) each having a periphery consisting of a free portion (4A) extending between the tips (3X) of posts (3) and a fixed portion (4B) secured and sealed to corresponding sides of the posts and the adjacent portion of the base. A bicuspid mitral valve replacement has a pair of posts (3) disposed at opposite ends of a diameter of the undistorted base (2), or displaced therefrom towards the portion (2A) of lesser flexibility to accommodate leaflets (4) of unequal size. The frame (1) is formed of Delrin covered with Dacron cloth, the Delrin having differing thicknesses to either side of the posts (3) which merge into the base (2) by way of a continuous curve (6) on each side. The leaflets (4) are cut from flat sheet in a special way to avoid stress-fixing.



EP 0 084 395 A1

ARTIFICIAL HEART VALVES

This invention relates to artificial heart valves and has for its object the provision of a bioprosthetic bicuspid or tricuspid mitral valve replacement affording a performance closely comparable to that of a natural mitral valve.

According to the present invention, a bioprosthetic mitral valve replacement comprises a flexible frame having a ring-shaped base and at least a pair of upstanding posts, which divide the base into at least two portions of varying flexibility, together with animal tissue leaflets each having a periphery consisting of a free portion extending between the tips of posts and a fixed portion secured and sealed to corresponding sides of the posts and the adjacent portion of the base.

In use in a heart, the ring-shaped base is attached to the circumference of the auriculo-ventricular orifice (preferably through an intermediate sewing ring) with the portion of the base of greater flexibility adjacent the aortic valve, whereby the base can deform from a substantially circular shape to an approximate D-shape, as is the case with

the natural mitral valve.

In a bicuspid mitral valve replacement a pair of posts may be disposed at opposite ends of a diameter of the undistorted base, or they may be displaced therefrom towards the portion of lesser flexibility to accommodate leaflets of unequal size, as in the natural mitral valve. In a tricuspid mitral valve replacement three posts may be disposed at regular intervals round the undistorted base, or at other intervals dictated, for example, by the anatomical requirements of coronary ostia in aortic valve replacements.

The flexible frame is preferably formed of Delrin (Registered Trade Mark) covered with Dacron (Registered Trade Mark) cloth, with the differential flexibility afforded by differing thicknesses of the frame material to either side of the posts. The posts preferably merge at each side into the respective arcuate portions of the ring-shaped base, with the merging preferably being by way of a continuous curve from the rounded tip of one post to the rounded tip of the other post.

The valve leaflets are preferably cut from a flat sheet of fully fixed (i.e.

gluteraldehyde treated) animal tissue (c.g. bovine or calf pericardium), but the shape of each leaflet preferably corresponds to a portion of a surface of a cone which portion is defined by the intersections on the conical surface of two parallel flat planes having peripheries on the conical surface corresponding in length respectively to the circumference of the ring-shaped base and the distance between the tips of the posts of the frame, and a third intersection on the conical surface of a curved plane concave towards the apex of the cone and intersecting the two parallel flat planes at opposite sides of the cone, the spacing of the flat planes and the curvature of the curved plane being such that the development of the curved plane on the conical surface matches in length and curvature the continuously blending curve of one arcuate portion of the ring-shaped base and the adjacent sides of the posts, so that no moulding or stress-fixing of the leaflet material is required.

Two embodiments of the invention and a slight modification of one, will now be described, by way of example only, with

reference to the accompanying drawings, in which:-

Figure 1 is a perspective view of a bicuspid mitral valve replacement in accordance with the invention;

Figure 2 is an underneath view or inflow aspect of the valve replacement of Figure 1;

Figures 3(a) and (b) are side elevations at  $90^{\circ}$  to each other of the frame of the valve replacement of Figures 1 and 2;

Figure 3(c) is an underneath view of Figure 3(a);

Figure 3(d) corresponds to Figure 3(c) but shows how the base can deform to a D-shape;

Figure 4 is a diagram illustrating how the shape of each leaflet of the valve of Figures 1 and 2 is derived;

Figure 5 corresponds to Figure 3(a) but shows the frame of a bicuspid mitral valve replacement with the posts displaced from the ends of the diameter of the base towards the portion of lesser flexibility;

Figure 6 is a perspective view of a tricuspid mitral valve replacement in

accordance with the invention;

Figure 7 is an underneath view or inflow aspect of the valve replacement of Figure 6;

5           Figure 8 is a diagram of a test rig for testing valves; and

Figure 9 is a comparative table of test results.

10           In Figures 1 to 3, a bioprosthetic bicuspid mitral valve replacement comprises a flexible plastics frame 1 (Figure 3) having a ring-shaped base 2 and a pair of upstanding posts 3 at opposite ends of a diameter and dividing the base into two portions 2A, 2B of  
15           varying flexibility, together with two animal tissue leaflets 4 (Figures 1 and 2) each having a periphery consisting of a free portion 4A extending between the tips 3X of the posts 3 and a fixed portion 4B secured and  
20           sealed to corresponding sides of the posts and the adjacent portion of the base.

25           The flexible frame 1 is formed of Delrin covered with Dacron cloth 5 (Figure 1), with the differential flexibility afforded by differing thicknesses of Delrin in the respective portions 2A, 2B of the base 2 into

which the posts 3 merge at each side by way of a continuous curve 6 from the rounded tip 3X of one post 3 to the rounded tip 3X of the other post 3.

5                Figures 1 and 2 show the leaflets 4 in their natural positions after attachment to the cloth-covered frame 1, which is shown stitched to a sewing ring 7 through which it can be attached to the circumference of the  
10                auriculo-ventricular orifice in a heart (not shown), with the portion 2B of the base 2 of greater flexibility adjacent the aortic valve, whereby the base can deform to an approximate D-shape (as shown by Figure 3) as is the case  
15                with the natural mitral valve.

                 The valve leaflets 4 are cut from a flat sheet of fully fixed (i.e. gluteraldehyde treated) animal tissue (e.g., bovine or calf pericardium) in the manner shown in Figure 4  
20                in which the shape of each leaflet 4 corresponds to a portion of the surface of a cone 8 which portion is defined by the intersections on the conical surface of two parallel flat planes 9, 10 having peripheries  
25                on the conical surface corresponding in length respectively to the circumference of the ring-



shaped base 2 and the distance between the tips 3X of the posts 3 of the frame 1, and a third intersection on the conical surface of a curved plane 11 concave towards the apex 12 of the cone 8 and intersecting the two parallel flat planes 9, 10 at opposite sides of the cone, the spacing of the flat planes and the curvature of the curved plane (which changes throughout its length) being such that the development 4B of the curved plane 11 on the conical surface matches in length and curvature the continuously blending curve 6 of one arcuate portion 2A or 2B of the ring-shaped base 2 and the adjacent sides of the posts 3, so that no moulding or stress-fixing of the leaflet 4 is required. References D,d and H,h in Figures 3 and 4 indicate corresponding diameters and heights respectively.

In Figures 3(a) and 3(b) the broken lines 4A' and 4A'' represent respectively the open positions and closed (or coaptation) positions of the free edges 4A of the leaflets 4.

As previously mentioned, and as will be seen in Figure 3 the posts 3 are disposed

at opposite ends of a diameter of the undistorted base 2; on the other hand, Figure 5 shows the posts 3 displaced towards the portion 2A of lesser flexibility to  
5 accommodate leaflets 4X, 4Y of unequal size, as in the natural mitral valve, in which case the leaflets are cut from flat sheet as in Figure 4 but with different cone angles appropriate to the respective leaflets.

10 In Figures 6 and 7 a bioprosthetic tricuspid mitral valve replacement comprises a flexible plastics frame 1 having a ring-shaped base 2 and three upstanding posts 3 disposed at regular intervals round the  
15 undistorted base, which has two portions 2A, 2B of varying flexibility, afforded by a greater thickness in the portion 2A than in the portion 2B, which latter is therefore more flexible, whereby the base can deform in the  
20 manner described with reference to Figure 3(d). Three animal tissue leaflets 4 each having periphery consist of a free portion 4A extending between the tips 3X of posts and a fixed portion 4B secured (after covering the  
25 frame 1 with cloth 5) and sealed to corresponding sides of the posts 3 and

adjacent portion of the base 2. The tricuspid valve replacement is shown with its leaflets 4 in their natural positions after attachment to the cloth covered frame 1, which is shown stitched to a sewing ring 7 through which it can be attached to the circumference of the auriculo-ventricular orifice in a heart (not shown), thereafter to function in similar manner to the bicuspid valve replacement of Figures 1 to 3. The three leaflets 4 of the tricuspid valve replacement are each cut from flat sheet as in Figure 4 but with different cone angle and diameters appropriate to the different lengths 4A and 4B.

In Figure 8, M and A represent test valves in the mitral and aortic positions respectively within a sealed test chamber 13 having an inlet fluid reservoir 14. Pumping is effected by a piston 15 with a velocity servo system 16 coupled to the digital/analogue (D/A) unit of a micro-computer 17, the flow being in the direction of the arrows from the aortic valve A to the mitral valve M via a lumped parameter model of afterload 18 and a turbine flowmeter 19.  $V_p$  and  $A_p$  are model ventricular and aortic

pressures respectively monitored with purpose  
built catheter tipped devices, Pd and Pv are  
the displacement and velocity respectively of  
the piston at any instant, and Vc is the  
5 piston control signal derived from the micro-  
computer 17 through its digital/analogue (D/A)  
unit.

A bicuspid mitral valve replacement in  
accordance with Figures 1 and 2 and two  
10 currently used tricuspid mitral valve  
replacements of corresponding size were tested  
for pressure drop and regurgitation in the  
mitral position M. A summary of the test  
results is given in the table of Figure 9 and  
15 shows that the performance of the new bicuspid  
valve replacement compares very favourably  
with the two currently available bioprosthetic  
tricuspid mitral valve replacements. In  
particular the comparison with the Ionescu-  
20 Shiley valve indicates similar pressure drops  
with appreciably less regurgitation.

CLAIMS

1. A bioprosthetic mitral valve replacement characterised by a flexible frame (1) having a ring-shaped base (2) and at least a pair of upstanding posts (3), which  
5 divide the base into at least two portions (2A, 2B) of varying flexibility, together with animal tissue leaflets (4) each having a periphery consisting of a free portion (4A) extending between the tips (3X) of posts (3) and a fixed portion (4B) secured and sealed to  
10 corresponding sides of the posts and the adjacent portion of the base.

2. A bicuspid mitral valve replacement as in Claim 1, characterised in that a pair of posts (3) are disposed at opposite ends of a diameter of the undistorted  
5 base (2).

3. A bicuspid mitral valve replacement as in Claim 1, characterised in that a pair of posts (3) are displaced from the opposite ends of a diameter of the undistorted base (2) towards the portion (2A)  
5 of lesser flexibility to accommodate leaflets (4) of unequal size.

4. A tricuspid mitral valve

replacement as in Claim 1, characterised in that three posts (3) are disposed at regular intervals round the undistorted base (2).

5        5. A mitral valve replacement as in any one of Claims 1 to 4, characterised in that the flexible frame (1) is formed of Delrin covered with Dacron cloth (5), with the differential flexibility afforded by differing thicknesses of frame material to either side of the posts (3).

6. A mitral valve replacement as in Claim 5, characterised in that the posts (3) merge at each side into the respective arcuate portions (2A, 2B) of the ring-shaped base (2).

5        7. A mitral valve replacement as in Claim 6, characterised in that the merging of the posts (3) into the base (2) is by way of a continuous curve (6) from the rounded tip (3X) of one post (3) to the rounded tip of the other post (10).




8. A mitral valve replacement as in Claim 7, characterised in that the valve leaflets (4) are cut from a flat sheet of fully fixed animal tissue.

9. A mitral valve replacement as in Claim 8, characterised in that the shape of




each leaflet (4) corresponds to a portion of a surface of a cone (8) which portion is defined by the intersections on the conical surface of two parallel flat planes (9, 10) having peripheries on the conical surface corresponding in length respectively to the circumference of the ring-shaped base (2) and the distance between the tips (3X) of the posts (3) of the frame (1), and a third intersection on the conical surface of a curved plane (11) concave towards the apex (12) of the cone (8) and intersecting the two parallel flat planes (9, 10) at opposite sides of the cone, the spacing of the flat planes (9, 10) and the curvature of the curved plane (11) being such that the development of the curved plane on the conical surface matches in length and curvature the continuously blending curve (6) of one arcuate portion (2A or 2B) of the ring-shaped base (2) and the adjacent sides of the posts (3).



1/4

**Fig. 3**








Fig. 7




Fig. 8

4/4

	PRIOR ART I IONESCU-SHILEY			PRIOR ART II HANCOCK			INVENTION FIGURES 1 & 2		
	Pressure Drop (mm Hg)		Regurgi- tation cm <sup>3</sup> /beat	Pressure Drop (mm Hg)		Regurgi- tation cm <sup>3</sup> /beat	Pressure Drop (mm Hg)		Regurgi- tation cm <sup>3</sup> /beat
	Mean	Maximum		Mean	Maximum		Mean	Maximum	
Mean Flow 180cm <sup>3</sup> /sec. Stroke Volume 65cm <sup>3</sup>	1.6	7.6	7.1	5.8	14.8	3.6	1.8	7.6	5.5
Mean Flow 225cm <sup>3</sup> /sec. Stroke Volume 81cm <sup>3</sup>	2.9	10.9	6.8	8.7	21.8	4.0	3.1	10.9	5.9
Mean Flow 272cm <sup>3</sup> /sec. Stroke Volume 98cm <sup>3</sup>	4.3	14.8	7.1	12.0	29.6	4.7	4.4	15.4	5.7

Fig. 9



European Patent  
Office

# EUROPEAN SEARCH REPORT

0084395

Application number

DOCUMENTS CONSIDERED TO BE RELEVANT			EP 83200046.7
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int. Cl. 3)
X,Y	<u>EP - A2 - 0 051 451</u> (SHILEY INC.) --	1,4,8	A 61 F 1/22
Y	<u>DE - B2 - 1 915 178</u> (CUTTER LABORATORIES INC.)	1,4,8	
A	* Fig. 3,4, pos. 34 * --	7	
A	<u>GB - A - 2 056 023</u> (ROSS; BODNAR) --	1,4,7,8	
A	<u>GB - A - 2 046 165</u> (ROSS, BODNAR) * Fig. 1,3 * --	1,4,7,8	
A	<u>GB - A - 1 538 204</u> (AMERICAN HOSPITAL SUPPLY CORPORATION) --	1,4,7,8	
A	<u>GB - A - 1 243 293</u> (HANCOCK) --	1,4,7,8	TECHNICAL FIELDS SEARCHED (Int. Cl. 3)
A	<u>US - A - 3 714 671</u> (EDWARDS et al.) --	1,4,5,7,8	A 61 F 1/00
A	<u>US - A - 3 739 402</u> (COOLEY et al.) --	1,2,3,7,8	
A	<u>FR - A1 - 2 433 933</u> (LIOTTA, FERRARI) -----		
The present search report has been drawn up for all claims			
Place of search VIENNA		Date of completion of the search 30-03-1983	Examiner EBERLE
<p>CATEGORY OF CITED DOCUMENTS</p> <p>X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document</p> <p>T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons &amp; : member of the same patent family, corresponding document</p>			